


Legrand Group Belgium Kouterveldstraat 9, 1831 Diegem


Tel.: (+32) 02 719 17 11 - Fax: (+32) 02 719 17 00

SWIFTS Kabelladder industrie





Ref.: ZL200G



| Hoogte 10 | 0 – Mediun | n duty Topaz | | | | | |
|-----------------|----------------|----------------------|-----------------|------------|------------|------------|------------|
| | | | | Ref. | Ref. | Ref. | Ref. |
| Breedte (mm) | Hoogte (mm) | Sportafstand (mm) | Gewicht (Kg) | GC | | 31 | 6L |
| | | | Lengte 3 m | Lengte 3 m | Lengte 6 m | Lengte 3 m | Lengte 6 m |
| 150 | 100 | 300 | 12,000 | ZL150G | ZL150G6M | ZL150S | ZL150S6M |
| 200 | 100 | 300 | 12,538 | ZL200G | ZL200G6M | ZL200S | ZL200S6M |
| 300 | 100 | 300 | 13,352 | ZL300G | ZL300G6M | ZL300S | ZL300S6M |
| 400 | 100 | 300 | 14,572 | ZL400G | ZL400G6M | ZL400S | ZL400S6M |
| 450 | 100 | 300 | 14,836 | ZL450G | ZL450G6M | ZL450S | ZL450S6M |
| 500 | 100 | 300 | 15,805 | ZL500G | ZL500G6M | ZL500S | ZL500S6M |
| 600 | 100 | 300 | 16,854 | ZL600G | ZL600G6M | ZL600S | ZL600S6M |

MATERIAALSOORTEN



Elektrolytisch verzinkt Norm EN ISO 2081




Sendzimir verzinkt Norm EN 10346



Poedercoat (gelakt)



Thermisch verzinkt Norm EN ISO 1461



RVS 304 L (Inox) Norm EN 10088-2




RVS 316 L (Inox) Norm EN 10088-2




Gemenied



Aluminium




| Hoogte 12 | 5 – Heavy | duty Sapphire | | | | | | | |
|-----------------|----------------|-------------------|-----------------|------------|------------|------------|------------|----|----|
| | | | | Ref. | Ref. | Ref. | Ref. | | |
| Breedte (mm) | Hoogte (mm) | Sportafstand (mm) | Gewicht (Kg) | GC | | GC | | 31 | 6L |
| | | | Lengte 3 m | Lengte 3 m | Lengte 6 m | Lengte 3 m | Lengte 6 m | | |
| 150 | 125 | 300 | 13,688 | PL150G | PL150G6M | PL150S | PL150S6M | | |
| 200 | 125 | 300 | 14,226 | PL200G | PL200G6M | PL200S | PL200S6M | | |
| 300 | 125 | 300 | 15,040 | PL300G | PL300G6M | PL300S | PL300S6M | | |
| 400 | 125 | 300 | 15,854 | PL400G | PL400G6M | PL400S | PL400S6M | | |
| 450 | 125 | 300 | 16,261 | PL450G | PL450G6M | PL450S | PL450S6M | | |
| 500 | 125 | 300 | 17,552 | PL500G | PL500G6M | PL500S | PL500S6M | | |
| 600 | 125 | 300 | 18,542 | PL600G | PL600G6M | PL600S | PL600S6M | | |
| 750 | 125 | 300 | 21,977 | PL750G | PL750G6M | PL750S | PL750S6M | | |
| 800 | 125 | 300 | 22,602 | PL800G | PL800G6M | PL800S | PL800S6M | | |
| 900 | 125 | 300 | 23,853 | PL900G | PL900G6M | PL900S | PL900S6M | | |
| 1000 | 125 | 300 | 25,104 | PL1000G | PL1000G6M | PL1000S | PL1000S6M | | |




| Hoogte 15 | Hoogte 150 – Extra heavy duty Emerald | | | | | | |
|-----------------|---------------------------------------|----------------------|-----------------|------------|------------|------------|------------|
| | | | | Ref. | Ref. | Ref. | Ref. |
| Breedte (mm) | Hoogte (mm) | Sportafstand (mm) | Gewicht (Kg) | GC | | 31 | 6L |
| | | | Lengte 3 m | Lengte 3 m | Lengte 6 m | Lengte 3 m | Lengte 6 m |
| 150 | 150 | 300 | 20,635 | EL150G | EL150G6M | EL150S | EL150S6M |
| 200 | 150 | 300 | 20,820 | EL200G | EL200G6M | EL200S | EL200S6M |
| 300 | 150 | 300 | 21,449 | EL300G | EL300G6M | EL300S | EL300S6M |
| 400 | 150 | 300 | 22,265 | EL400G | EL400G6M | EL400S | EL400S6M |
| 450 | 150 | 300 | 22,670 | EL450G | EL450G6M | EL450S | EL450S6M |
| 500 | 150 | 300 | 23,961 | EL500G | EL500G6M | EL500S | EL500S6M |
| 600 | 150 | 300 | 24,951 | EL600G | EL600G6M | EL600S | EL600S6M |
| 750 | 150 | 300 | 28,386 | EL750G | EL750G6M | EL750S | EL750S6M |
| 800 | 150 | 300 | 29,010 | EL800G | EL800G6M | EL800S | EL800S6M |
| 900 | 150 | 300 | 30,262 | EL900G | EL900G6M | EL900S | EL900S6M |
| 1000 | 150 | 300 | 31,513 | EL1000G | EL1000G6M | EL1000S | EL1000S6M |

Bovenstaande artikelnummers zijn standaard beschikbaar. Voor afwijkende kleuren, lengtes, breedtes of vormen (bijvoorbeeld afwijkend perforatiepatroon) informeer voor mogelijkheden bij Salessupport van Legrand.


Swifts® straight lengths medium duty (Topaz)




■ Dimensions and weights



Dimensions





Weights

| Width (W) | Cat. Nos. | Weight (kg) |
|--------------|-----------|-------------|
| 150 | ZL 150 F | 12·1 |
| 300 | ZL 300 F | 13-4 |
| 450 | ZL 450 F | 14.6 |
| 600 | ZL 600 F | 16-9 |
| 750 | ZL 750 F | 20.3 |
| 900 | ZL 900 F | 22.2 |

All weights given are in kilograms (kg) and are for a 3 m straight length in hot dip galvanised G finish To obtain the appropriate

component weight in other finishes, multiply the given weight by the following factors:

(D) x 1·07 (S) x 0·94 (E) x 0·97 Deep galvanised Stainless steel Powder coated

Gauge

Standard side rail = 1.5 mm

Key: Replace the letter shown in red with your choice from the following options :

F = Finish : G (hot dip galvanised after manufacture)


(deep galvanised) (stainless steel) E (powder coated)


■ Loading graphs

Load tests carried out to BS EN 61537 test type 1 (safety factor 1.7+ and joint in middle of span) or test type 4 (safety factor 1.7+ and joint in middle of span with rung slot over support)

Load tests carried out over 2 m, 3 m and 4 m spans using 3 m lengths Safe working load should include all cable loads and any other additional loads (e.g. wind, snow)

When installed, inner span deflection will vary depending on joint positions but will typically be about half of test end span deflection





Graph showing safe working load vs span with deflections shown at SWL

■ Finishes

Standard stocked finish:

Hot dip galvanised after manufacture to BS EN ISO 1461: 2009


Additional finishes:

- Deep galvanised high silicon steel made from BS EN 10025-5 : 2004 Grade S355JOWP D
- s Stainless steel to BS EN 10088 - 2 grade 1.4404
 - (equivalent to 316L31)
 Pickle and passivation is available to special order
- Е Powder coated (to customer's specification)




Sheared steel (particularly stainless steel) does have relatively sharp edges and protective gloves must be worn during handling

All dimensions (mm) are nominal




Coupler sets: see p. 7-13


Swifts® straight lengths heavy duty (Sapphire)




■ Dimensions and weights



Dimensions



Standard length = 3000 mm (6000 mm available on special request)



Weights

| Width (W) | Cat. Nos. | Weigh |
|--------------|-----------|-------|
| 150 | PL 150 F | 13.8 |
| 300 | PL 300 F | 15.0 |
| 450 | PL 450 F | 16.3 |
| 600 | PL 600 F | 18.5 |
| 750 | PL 750 F | 22.0 |
| 900 | PL 900 F | 23.9 |

All weights given are in kilograms (kg) and are for a 3 m straight length in hot dip galvanised G finish

To obtain the appropriate component weight in other finishes, multiply the given weight by the following factors

| 07 |
|----|
| 94 |
| 97 |
| ֡ |

■ Loading graphs


Load tests carried out to BS EN 61537 test type 1 (safety factor 1·7+ and joint in middle of span) or test type 4 (safety factor 1·7+ and joint in middle of span with rung slot over support)


Load tests carried out over 3 m, 4 m and 5 m spans using 3 m lengths and 6 m spans using 6 m lengths

Safe working load should include all cable loads and any other additional loads (e.g. wind, snow)

For spans greater than 5 m : data is for 6 m long ladders only For spans 5 m and less : data can be used for 3 m or 6 m long lengths For spans greater than 5 m: ladder is not suitable for use with dynamic loads (e.g. wind, snow)

When installed, inner span deflection will vary depending on joint positions but will typically be about half of test end span deflection





Graph showing safe working load vs span with deflections shown at SWL

(1) Deflections shown for G finish. D and S finish deflections on application, please contact Legrand

Standard stocked finish:

Hot dip galvanised after manufacture to BS EN ISO 1461: 2009

Additional finishes :

- Deep galvanised high silicon steel made from BS EN 10025-5: 2004 Grade S355JOWP Stainless steel to BS EN 10088 2 grade 1·4404 (equivalent to 316L31) s Pickle and passivation is available to special order
 - Powder coated (to customer's specification)



Ε

Sheared steel (particularly stainless steel) does have relatively sharp edges and protective gloves must be worn during handling

Gauge

Standard side rail = 1.5 mm Non-standard side rail = 2.0 mm


Replace the letter shown in red with your choice from the following options:

= Finish : G (hot dip galvanised after manufacture)

(deep galvanised) (stainless steel)

(powder coated)


All dimensions (mm) are nominal




Coupler sets: see p. 7-13

Swifts® straight lengths extra heavy duty (Emerald)






Dimensions



Standard length = 3000 mm (6000 mm available on special request)



Weights

| Width (W) | Cat. Nos. | Weight (kg) |
|--------------|-----------|-------------|
| 150 | EL 150 F | 20.7 |
| 300 | EL 300 F | 22.1 |
| 450 | EL 450 F | 23.5 |
| 600 | EL 600 F | 25.0 |
| 750 | EL 750 F | 28.8 |
| 900 | EL 900 F | 30.8 |


All weights given are in kilograms (kg) and are for a 3m straight length in hot dip galvanised G finish

To obtain the appropriate component weight in other finishes, multiply the given weight by the following factors:

(D) (S) (E) x 1·07 Deep galvanised Stainless steel x 0.94 Powder coated x 0.97

Gauge

Standard side rail = 2.0 mm



Load tests carried out to BS EN 61537 test type 1 (safety factor 1.7+ and joint in middle of span) or test type 4 (safety factor 1.7+ and joint in middle of span with rung slot over support)

Load tests carried out over 3 m, 4 m and 5 m spans using 3 m lengths and 6 m spans using 6 m lengths


Safe working load should include all cable loads and any other additional loads (e.g. wind, snow)

For spans greater than 5 m : data is for 6 m lengths only For spans 5 m and less : data can be used for 3 m or 6 m lengths

For spans greater than 5 m: ladder is not suitable for use with dynamic loads (e.g. wind, snow)

When installed, inner span deflection will vary depending on joint positions but will typically be about half of test end span deflection shown below

End span deflection at Max. SWL (mm)(1)



Graph showing safe working load vs span with deflections shown at SWL

(1) Deflections shown for G finish. D and S finish deflections on application, please contact Legrand

■ Finishes

Standard stocked finish:

Hot dip galvanised after manufacture to BS EN ISO 1461: 2009

Additional finishes:

- Deep galvanised high silicon steel made from BS EN 10025-5 : 2004 Grade S355JOWP
- Stainless steel to BS EN 10088 2 grade 1.4404 S (equivalent to 316L31)
 - Pickle and passivation is available to special order
- Powder coated (to customer's specification)



Sheared steel (particularly stainless steel) does have relatively sharp edges and protective gloves must be worn during handling


Replace the letter shown in red with your choice from the following options:

= Finish: G (hot dip galvanised after manufacture)

(deep galvanised) (stainless steel)

(powder coated)

All dimensions (mm) are nominal



Coupler sets: see p. 7-13

Swifts® cable ladder rungs for straight lengths and fittings

■ Rung details


Type 1 rungs are used as standard

Type 2 and 3 are only available to special order Type 3 is not available in deep galvanised finish Types 1 and 3 can be supplied in any combination to special order

Options and dimensions


Standard

Type 1




Special order only

Type 2



Type 3



Slot pattern may differ on stainless steel type 3 rungs Contact Legrand


Swifts® cable ladder systems diagonal bracing – straight lengths

■ Diagonal bracing

The effect of lateral loads on spans over 5 m or 6 m can be much reduced by adding diagonal bracing

Bracing is achieved by fitting a ladder Type 1 rung section, cut to length from a 3 m length supplied, diagonally across the underside of the ladder as shown in the illustration below. Diagonal bracing can be fitted to either heavy duty (Sapphire) or extra heavy duty (Emerald) ladders – medium duty (Topaz) is not suited to these long spans


■ Installation (typical)



Couplers are best located over the point of support to provide additional local reinforcement of the ladder side rails. Details on long span installations are given on p. 129

■ Assembly

Fasteners (not included)



- A M10 Swiftrack channel nut (PN 100)
- B Ladder rung
- 40 x 40 x 6 square washer, Cat. No. SB506/10
- D Diagonal brace (type 1 rung)
- M10 form A washer Ε
- M10 x 25 Grade 8.8 setscrew hot dip galvanised

Fastener finishes

For ladders with S finish, fasteners are corrosion resistant stainless Grade A470

All dimensions (mm) are nominal

Swifts® cable ladder couplers and fasteners straight length to straight length couplers


Couplers are used for joining together straight lengths in the medium duty (Topaz), heavy duty (Sapphire) and extra heavy duty (Emerald)


Fittings in these ranges have integral couplers. See p. 7 for more information


Even when ladders are cut to length, the slots in the coupler will always align with the slots in the ladder side rail

Supplied in pairs with the appropriate quantity of fasteners

■ Installation (typical)







Joggles are formed in the bottom of PC and EC couplers to allow easy installation of ladder cut lengths

Key: Replace the letter shown in red with your choice from the following options:


= Finish: G (hot dip galvanised after manufacture)

(deep galvanised) (stainless steel)

E (powder coated)


100 ີ 125





■ Assembly

Slide the couplers under the return flanges of one ladder side rail and loosely fit a single fastener to each coupler to hold it in place Slide the second ladder over both couplers, adjust each coupler position to align the slots with the side rail slots and secure with all fasteners



Note

Bolts should be inserted through the side rail first For location of coupler and position of fasteners, see below

Fastener positioning

Medium duty (Topaz)

Supplied in pairs, with fasteners (4 per coupler)



When bolting to cut ends adjust coupler to ensure 4 bolts can be

Note

When connecting straight lengths to straight lengths even when ladder is cut to length, the slots in the coupler will always align with slots in the ladder side rail

Heavy duty (Sapphire) and extra heavy duty (Emerald)

Supplied in pairs, with fasteners (8 per coupler)



When bolting to cut ends adjust coupler to ensure 8 bolts can be inserted Note

When connecting straight lengths to straight lengths even when ladder is cut to length, the slots in the coupler will always align with slots in the ladder side rail

| | Topaz | _adder rang Sapphire | e Emerald |
|-----------------------------------|-------|---------------------------|--------------|
| Cat. Nos. | ZCF | PCF | ECF |
| Quantity of fasteners per coupler | 4 | 8 | 8 |

When connecting straight lengths to fittings, use fastener sets, see p. 44

For additional types of straight length to straight length couplers and fasteners, see p. 7-13


All dimensions (mm) are nominal



Finishes and standards: see p. 14-16

■ Assembly (continued)

Fasteners (included)



- A Side rail
- B Coupler
- C M10 x 20 coachbolt D M10 flange nut

Recommended Torque Setting (M10): 40Nm


Fastener finishes

For ladders with G, D and E finishes, fasteners are high tensile Grade 8.8 hot dip galvanised


For ladders with S finish, fasteners are corrosion resistant stainless Grade A470

An alternative material for fasteners may be required depending on the installation environment - contact Legrand

■ Dimensions and weights







| Cat. Nos. | А | В | С | D | Weight (kg) |
|-----------|-----|----|-----|-----|-------------|
| ZCF | 220 | 13 | 95 | 1.5 | 0.6 |
| PCF | 220 | 13 | 119 | 2.0 | 1.0 |
| ECF | 220 | 13 | 144 | 2.0 | 1.2 |

Weights
All weights given are in kilograms (kg) and are for a pair of couplers in hot dip galvanised G finish
To obtain the appropriate component weight in other finishes, multiply the given weight by the following factors:

Deep galvanised (D) x 1·07
Stainless steel (S) x 0·94
Powder coated (E) x 0·97

All dimensions (mm) are nominal

Swifts® cable ladder couplers and fasteners


flexible expansion couplers


Flexible expansion couplers can be used to:

- a. provide a semi-flexible joint where ladder runs span separate structures between which some relative movement is possible
- b. provide compensation for changes in the length of a straight cable ladder run due to temperature variations

Supplied in pairs with fasteners

■ Installation (typical)





Flexible expansion couplers should normally be installed with the ridges facing outward, away from the bed of the ladder

If necessary, the stiffness of each joint can be increased by mounting pairs of couplers back-to-back (with one set of ridges facing inwards and the other set facing outwards as shown above) on either side of the cable ladder. The allowance for differential movement remains unchanged (see below)

Rigid support for the cable ladder should be provided on both sides adjacent to each joint

■ Assembly

Each joint formed by flexible expansion couplers provides for up to 10 mm of linear movement between the two adjacent ladders

To calculate the ideal distance between flexible expansion coupler installations use the formula : $L = K_S$

Where : L = distance between flexible expansion couplers, in metres $K_S = 909$ for mild steel, 625 for stainless steel T = temperature range (in °C) for which allowance is to be

made

Note

Coefficients of linear expansion: mild steel = 11 x 10⁻⁶/ °C

stainless steel = 16×10^{-6} / °C

Key: Replace the letter shown in red with your choice from the following options:

= Finish: G (hot dip galvanised after manufacture)

(deep galvanised)


(stainless steel)

E (powder coated)



■ Assembly (continued)

Fasteners (included)



- A Side rail
- В Coupler
- C M10 x 20 coachbolt
- D M10 flange nut

Recommended Torque Setting (M10): 40Nm

Fastener finishes

For ladders with G, D and E finishes, fasteners are high tensile Grade 8.8 hot dip galvanised


For ladders with S finish, fasteners are corrosion resistant stainless

An alternative material for fasteners may be required depending on the installation environment - contact Legrand

| | Ladder range Topaz ∣ Sapphire ∣ Emerald | | | | |
|---|--|-----|-----|--|--|
| | Topaz Sappnire Emeraid | | | | |
| Cat. Nos. | ZEF | PEF | EEF | | |
| Quantity of fasteners per coupler ⁽¹⁾ | 4 | 8 | 8 | | |

(1) for normal installation, or per pair (each side) for stiffened installation

Dimensions and weights



| Cat. Nos. | A | В | С | D | Weight (kg) |
|-----------|-----|-----|-------|-----|-------------|
| ZEF | 320 | 84 | 113.0 | 1.0 | 0.6 |
| PEF | 317 | 115 | 111.5 | 1.5 | 1.1 |
| EEF | 317 | 138 | 111.5 | 1.5 | 1.4 |


Weights

All weights given are in kilograms (kg) and are for a pair of couplers in hot dip galvanised G finish

To obtain the appropriate component weight in other finishes, multiply the given weight by the following factors:

Deep galvanised (D) x 1·07 (S) x 0·94 (E) x 0·97 Stainless steel Powder coated

All dimensions (mm) are nominal



Swifts® cable ladder couplers and fasteners bendable connectors


100 ີ 125 150

Bendable connectors can be used for :

- a. fabricating fittings on site from cut lengths of cable ladder
- b. reducing width of a run to the next size down when a properly manufactured reducer is not available
- c. correcting minor mis-alignment problems
- d. coupling lengths of ladder to form articulated bends


Bendable connectors are supplied in pairs with fasteners

■ Installation (typical)



Bending the run

Re-aligning the run



Note

Rigid support for the cable ladder should be provided on both sides adjacent to each joint

Key: Replace the letter shown in red with your choice from the following options:


= Finish: G (hot dip galvanised after manufacture)

D (deep galvanised)

(stainless steel) E (powder coated)

■ Assembly

Fasteners (included)



- A Side rail
- B Coupler
- C M10 x 20 coachbolt
- D M10 flange nut

Recommended Torque Setting (M10): 40Nm

Fastener finishes


For ladders with G, D and E finishes, fasteners are high tensile Grade 8.8 hot dip galvanised

For ladders with S finish, fasteners are corrosion resistant stainless

An alternative material for fasteners may be required depending on the installation environment - contact Legrand

| | Ladder range Topaz Sapphire Emerald | | | | | |
|--|--|-----|-----|--|--|--|
| Cat. Nos. | ZHF | PHF | EHF | | | |
| Quantity of fasteners per connector | 4 | 8 | 8 | | | |
| per additional connector | 2 | 4 | 4 | | | |

■ Dimensions and weights



| Cat. Nos. | Α | В | С | Weight (kg) |
|-----------|-----|-----|-----|-------------|
| ZHF | 250 | 84 | 1.5 | 0.5 |
| PHF | 250 | 115 | 1.5 | 0.7 |
| EHF | 250 | 140 | 1.5 | 0.8 |

All weights given are in kilograms (kg) and are for a pair of couplers in hot dip galvanised G finish

To obtain the appropriate component weight in other finishes, multiply the given weight by the following factors :

Deep galvanised Stainless steel

(D) x 1·07 (S) x 0·94 (E) x 0·97

Powder coated

All dimensions (mm) are nominal

Straight lengths: see p. 14-16

Swifts® cable ladder couplers and fasteners

vertical hinged connectors


Vertical hinged connectors can be used for :

- a. fabricating fittings on site from cut lengths of cable ladder
- b. solving minor vertical mis-alignment problems
- c. coupling articulated risers to adjacent ladders

Supplied in sets comprising four plates and fasteners

■ Installation (typical)

Heavy duty (Sapphire) PVF (ZVF and EV similar)



■ Assembly


Vertical hinged connectors can either be connected together to form pre-set angles or pre-assembled for adjustment in situ

Assembly to a pre-set angle

- 1. identify the correct outer fixing holes for the required pre-set angle (see table and illustration below)
- 2. insert a fastener through the identified holes in both plates and fit a locking washer and nut but do not fully tighten Do not insert fasteners through the centre hole first, this makes identification of the outer holes very difficult
- 3. move the two connectors to align the centre holes. Insert a fastener through the holes and fit a locking washer and nut **but do not fully**
- insert a third fastener through a slot in one connector and an aligning hole in the other. Fit a locking washer and nut
- 5. tighten all fasteners

| Cat. Nos. | 15° | 18° | 22·5° | 30° | 45° |
|---------------|-----|-------|-------|-------|-----|
| ZVF, PVF, EVF | G:C | A : F | E:B | B : G | F:C |

ZVF, PVF, EVF






Pre-assembly for adjustment in-situ

- 1. insert a fastener through the outer hole of both connectors. Fit a locking washer and nut and tighten sufficiently to hold the assembly together while it is carried to the installation position
- 2. fit the assembly to the installed ladders
- insert a second fastener through the slot in one connector and an aligning hole and fit a locking washer and nut
- if possible, insert a third fastener through either the alternate slot and an aligning hole, or two aligning holes. Fit a locking washer and nut
- 5. tighten all fasteners

Connector to ladder fasteners (included)




- A Side rail
- **B** Connector
- C M10 x 20 coachbolt
- D Flange nut

Key: Replace the letter shown in red with your choice from the following options

- = Finish: G (hot dip galvanised after manufacture)
 - (deep galvanised)
 - (stainless steel)
 - E (powder coated)







■ Assembly (continued)

Connector to connector fasteners (included)

PVF, EVF

- A M6 x 16 setscrews
- B M6 washer
- C M6 shakeproof washer
- D Connector
- E M6 nut
- F M10 x 20 setscrews
- G M10 form A washer
- H Flange nut

В **Recommended Torque** Setting (M10): 40Nm

Fastener finishes


ABD


For ladders with G and D finishes, fasteners are high tensile Grade 8.8 For ladders with S finish, fasteners are corrosion resistant stainless Grade A470

For ladders with E finish, the fasteners are Grade 8.8 hot dip galvanised An alternative material for fasteners may be required depending on the installation environment - contact Legrand

| | Ladder range Topaz Sapphire Emerald | | | |
|--|--|---------|---------|--|
| Cat. Nos. | ZVF | PVF | EVF | |
| Quantity of fasteners per connector to ladder | 2 x M10 | 4 x M10 | 4 x M10 | |
| per connector to connector | 3 x M6 | 3 x M10 | 3 x M10 | |

■ Dimensions and weights





| Cat. Nos. | Α | В | С | D | E | Weight (kg) |
|-----------|-----|-----|-------|------|-----|-------------|
| ZVF | 212 | 80 | 172.0 | 50.0 | 1.5 | 0.8 |
| PVF | 250 | 115 | 192.5 | 71.0 | 2.0 | 1.5 |
| EVF | 270 | 140 | 201.0 | 79.5 | 2.0 | 2.0 |

Weights

All weights given are in kilograms (kg) and are for a set of four plates in hot dip galvanised G finish

To obtain the appropriate component weight in other finishes, multiply the given weight by the following factors:

Deep galvanised Stainless steel Powder coated

(D) x 1·07 (S) x 0·94 (E) x 0·97

Finishes and standards: see p. 14-16

Swifts® cable ladder couplers and fasteners

integral fitting couplers and fitting to fitting couplers

125 150

■ Integral fitting couplers

All ladder fittings have integral couplers For straight length to fitting connections, see below For fitting to fitting connections, see opposite

■ Assembly

For straight length to fitting connections, use fasteners sets, see table below for number of fasteners required per fitting type For fitting to fitting couplers, see opposite

Fastener positioning Medium duty (Topaz)



Heavy duty (Sapphire) and extra heavy duty (Emerald)




Fastener sets comprise 50 of each of the following: M10 coach bolt and flange nut

| Number of fasteners required per fitting type Topaz Sapphire and Emerald | | | | | |
|--|----|----|--|--|--|
| Flat bends | 8 | 16 | | | |
| Inside / outside risers | 8 | 16 | | | |
| Reducers | 8 | 16 | | | |
| Tees | 12 | 24 | | | |
| 4 way crosspieces | 16 | 32 | | | |


Fastener detail and finishes, see opposite

■ Dimensions


Medium duty (Topaz) end detail



Heavy duty (Sapphire) end detail




Extra heavy duty (Emerald) end detail





■ Fitting to fitting couplers

Fitting to fitting couplers are used for joining together cable ladder fittings (bends, tees, risers etc) in the medium duty (Topaz), heavy duty (Sapphire) and extra heavy duty (Emerald) ranges. Fittings in these ranges have integral couplers. See opposite for more information. Supplied in pairs with the appropriate quantity of fasteners

■ Installation (typical)







Key: Replace the letter shown in red with your choice from the following options:

F = Finish: G (hot dip galvanised after manufacture)


(deep galvanised) (stainless steel) E (powder coated)

All dimensions (mm) are nominal

Finishes and standards: see p. 14-16

■ Assembly

Slide the couplers under the return flanges of one ladder side rail and loosely fit a single fastener to each coupler to hold it in place Slide the second ladder over both couplers, adjust each coupler position to align the slots with the side rail slots and secure with all fasteners




Note

For location of coupler and position of fasteners, see below

Fastener positioning


Medium duty (Topaz)

Supplied in pairs, with fasteners (4 per coupler)



Heavy duty (Sapphire) and extra heavy duty (Emerald)

Supplied in pairs, with fasteners (8 per coupler)




| | Ladder range Topaz Sapphire Emerald | | | |
|-----------------------------------|--|------|------|--|
| Cat. Nos. | ZFCF | PFCF | EFCF | |
| Quantity of fasteners per coupler | 4 | 8 | 8 | |

Note

When connecting straight lengths to fittings, use fastener sets, see opposite

Fasteners (included)



- A Side rail
- B Coupler
- C M10 x 20 coachbolt
- D M10 flange nut

Recommended Torque Setting (M10): 40Nm

Fastener finishes


For ladders with G, D and E finishes, fasteners are high tensile Grade 8.8 hot dip galvanised

For ladders with S finish, fasteners are corrosion resistant stainless Grade A470


An alternative material for fasteners may be required depending on the installation environment - contact Legrand

■ Dimensions and weights


Medium duty (Topaz) ZFCF



Heavy duty (Sapphire) PFCF



Extra heavy duty (Emerald) EFCF



| Cat. Nos. | Weight (kg) |
|-----------|-------------|
| ZFCF | 0.6 |
| PFCF | 1.1 |
| EFCF | 1.4 |

Weights

All weights given are in kilograms (kg) and are for a pair of couplers in hot dip galvanised G finish

To obtain the appropriate component weight in other finishes, multiply the given weight by the following factors:

Deep galvanised (D) x 1·07 Stainless steel (S) x 0·94 Powder coated (E) x 0·97

Finishes

IN THIS SECTION...

- 1. British standards
- 2. Hot dip galvanised (G) = thermisch verzinkt
- 3. Deep galvanised (D)
- 4. Pre-galvanised (PG) = sendzimir verzinkt
- 5. Stainless steel (S)
- 6. Powder coated (E)

British standards

Legrand ensures that all of the materials used during the construction and finishing of their products conform to the relevant standards.

In particular, the relevant standards for steel are:

| Finish | Product | Current standard/grade |
|--------|------------------------------|--|
| G | Ladder less than 1.5mm thick | BS EN 10130 : 2006 Grade DC01 |
| G | Ladder 1.5mm and thicker | BS EN 10111 : 1998 Grade 1.0332 / BS EN 10025 : 2004 Grade S275JRC |
| G | Swiftrack channel | BS EN 10025 : 1993 Grade S235JRC (Ys = 250N/mm² min) |
| G | Swiftrack brackets | BS EN 10025 : 2004 Grade S275JRC |
| PG | Swiftrack channel | BS EN 10346 : 2009 Grade S250GD + Z275 |
| D | Ladder | BS EN 10025-5 : 2004 Grade S355JOWP |
| S | Ladder and Swiftrack | BS EN 10088 : 2005 Grade 1.4404 (equivalent to S316L31) |

Finishes:

G = hot dip galvanised after manufacture

PG = pre-galvanised

D = deep galvanised

S = stainless steel E = powder coated

2 Hot dip galvanised (G)

Hot dip galvanising after manufacture is an excellent, economical protective finish used on support systems in many industrial and commercial applications.

Background

The galvanised coating is applied as a final manufacturing process by immersing a steel component (after various pre-treatments) in a large bath of molten zinc; the zinc forms an alloy with the steel substrate and protects the steel from corrosion in two ways. Firstly, the zinc coating surrounds the base steel with a total, tough physical barrier preventing corrosion of the steel by the surrounding atmosphere. Secondly, if steel does become exposed, e.g. at a cut edge, the zinc coating acts as a sacrificial anode and will be gradually corroded in preference to the underlying steel. Corrosion products from the zinc will also be deposited onto the steel, effectively re-sealing the surface and maintaining the integrity of the barrier.

The life of a zinc coating is directly proportional to its thickness but in different environments this life does vary. However because hot dip galvanising has been used for many years its life in diverse environments has been well established. The most comprehensive guide to the design life of protective systems in different environments is contained in BS EN ISO 12944-5: 2007 'Paints and varnishes' and BS EN ISO 14713: 2009 'Parts 1 + 2 - zinc coatings'. In the presence of certain atmospheric pollutants (such as sulphur dioxide in industrial areas) or when installed in an aggressive coastal or marine environment the rate of dissipation of the zinc will be accelerated; however in most situations hot dip galvanising remains an extremely effective and economical corrosion resistant finish.

Specification

BS EN ISO 1461 provides the specification for a hot dip galvanised coating. Heavier gauges of steel will usually take up a thicker coating of zinc than lighter gauges so the standard defines the coating for different steel gauges in terms of the weight of zinc per square metre of surface area. Ensuring compliance with this standard is obviously important. Unfortunately it is not reasonable to use this weight principle for checking the coating weight on components which have already been galvanised as it involves calculating the surface area then weighing a component, destructively removing the coating by chemical means and then re-weighing the component. It is therefore usual to measure instead the coating thickness (which can be done non-destructively using magnetic or electronic instruments) at a number of points on the surface of a component. The coating thicknesses given in the standard and their equivalent coating weights are shown in table 1.

Table 1 **Galvanising standard BS EN ISO 1461 : 2009**Minimum average zinc thickness

| Steel thickness | Minimum average zinc thickness (microns) |
|---|--|
| Less than 1.5 mm 1.5 mm and thicker up to 3 mm 3 mm and thicker but less than 6 mm 6 mm and thicker | 45 55 70 85 |

Note

For threaded and very small components which are spun galvanised, thinner coatings are used as recommended by BS EN ISO 1461.

It is important to distinguish between 'hot dip galvanised after manufacture to BS EN ISO 1461' and less precise descriptions such as 'galvanised', 'mill galvanised' or even the term 'hot dip galvanised', when used without reference to any standard. Mill galvanised steel is frequently used as an alternative finish for many support system components (see 'pre-galvanised steel', p. 120), and is available from Legrand, but this material does have a much thinner zinc coating which renders it unsuitable for exposed applications.

Suggested specification text: "All components should be not dip galvanised after completed manufacture to the requirements of BS EN ISO 1461."

Deep galvanised (D)

A deep galvanised finish has all of the characteristics of hot dip galvanising but with a much thicker coating of zinc. This gives 2-3 times the life of the standard hot dip galvanised (BS EN ISO 1461) finish

Background

The life of a galvanised coating depends very much upon the degree of pollution of the surrounding atmosphere; in an industrial or marine environment corrosion of the zinc may take place at double or treble the rate which would occur in an inland environment. Thus, if heavy atmospheric pollution or aggressive conditions exist in the vicinity of an installation, it is well worth considering the benefits provided by deep galvanising. Since this finish is produced in the same basic process as normal hot dip galvanising the initial cost premium of the material is relatively low; however the site installation costs will remain unchanged. Therefore, for a relatively modest premium on the overall installed cost the life of the installation can be increased dramatically.

Specification

Although the appropriate British Standard for deep galvanising is BS EN ISO 1461 (the same as for hot dip galvanising after manufacture) the process requires the use of steel containing a slightly higher proportion of silicon; often referred to as high silicon steel. When galvanising normal mild steel the process effectively ceases after a short immersion time in the galvanising bath, giving, depending on the gauge of the steel, the coating thicknesses laid down within BS EN ISO 1461. However with silicon bearing steels the chemistry of the galvanising process changes, resulting in the zinc coating continuing to increase in thickness as long as the steel remains immersed in the zinc. Coatings up to three times as thick as the minimum requirements of BS EN ISO 1461 are both possible and practical to achieve. However the most cost effective coating thickness is usually twice the thickness required by BS EN ISO 1461.

Pre-galvanised (PG)

A zinc coating can be economically applied to steel sheet immediately after its manufacture; the result, pre-galvanised steel (to BS EN 10346) can be an attractive, bright material which is suitable for non-arduous environments.

Background

Pre-galvanised (or mill galvanised) steel is produced by unwinding steel coil and passing it continuously through a bath of molten zinc and then past air jets to remove excess zinc from the surface. The process is closely controlled to produce a thin, even and ripple-free zinc coating with very few imperfections.

Because this pre-galvanised steel coil must then be cut to shape during subsequent manufacture of support equipment, the edges of the finished components will have no zinc coating; this aspect, together with the relatively light zinc coating provided by the process, make pre-galvanised services supports suitable for indoor, non-corrosive environments (particularly where an aesthetically attractive appearance is important) but unsuitable for humid indoor or outdoor applications.

Specification

For steel for Swiftrack channel, steel grade is BS EN 10346 : 2009 Grade S250GD + Z275

5 Stainless steel (S)

For all practical purposes most stainless steel services supports can be regarded as maintenance free and suffering no corrosion. Inevitably there is a relatively high price to pay for these attractive properties but, in aggressive environments or where the cost or inconvenience of gaining subsequent maintenance access is prohibitive, this initial cost premium may well be justified.

Background

Stainless steel contains a high proportion of chromium (usually at least 17%) and the steel's remarkable immunity to corrosive attack is conferred by the chromium-rich oxide film which occurs naturally on its surface. This invisible film is not only inert and tightly bonded to the surface, it also re-forms quickly if the surface is damaged in any way.

The fire resistance of stainless steel is particularly noteworthy; tests have demonstrated that stainless steel cable supports can be expected to maintain their integrity for considerable periods even when exposed to direct flame temperatures exceeding 1,000°C. This may be an important consideration where the electrical circuits being supported provide for emergency power or control systems.

Stainless steel is also used where hygiene is a major consideration. Its advantages in such applications are again its excellent resistance to the various chemicals and washes which are frequently used for cleaning purposes and the smoothness of surface (depending on the finish specified) which minimises the soiling or contamination that can take place.

Specification

Many grades of stainless steel are available but the one generally used in aggressive marine environments is BS EN 10088 Grade 1-4404 (equivalent to S316L31, BS 1449: Part 2). This grade has improved corrosion resistance (particularly in the presence of chlorides) and high temperature strength. It is much used in the chloride-laden marine conditions which exist on offshore installations and in coastal regions.

For less aggressive environments BS EN 10088 Grade 1-4301 (equivalent to 304, BS 1449: Part 2) is the normal grade. This grade offers good corrosion resistance in internal applications and also has a good aesthetic quality, often used in the dairy and food industries. Final finishes with mechanical brushing or polishing are often used to provide a good looking and robust surface finish.

Pickling and passivation

A stainless steel surface will have excellent corrosion resistance due to the chromium oxide layer on the surface of the product. With some stainless steels however, the surface areas can become subject to corrosion due to the depletion of chromium during welding, or the introduction of iron during a machining process (not applicable to most cable management products). Where a uniform appearance is important after carrying out welding processes, it is often specified that all surfaces should be pickled and passivated to remove the smoke stain from the welding process. Also where extreme corrosion resistance is called for, this process may help to remove crevice corrosion from around the welding area. Experience has shown that this is not normally necessary for the majority of cable management products.

Pickling

The pickling process involves the article being immersed in a blend of acids which dissolve iron and iron oxides which adhere to, or are embedded in, the surface of the stainless steel. These acids cause a removal of the surface layer of between 1 and 3 microns. The article is finally rinsed with water to complete this stage of the process.

Passivation

Passivation of the stainless steel will occur naturally after pickling when the oxygen in the air will react with the surface of the steel to form a passive chromium oxide layer. However it is usual for this passivation process to be speeded up by immersing the article in a nitric acid or other passivating agent.

Pickle and passivation is available as a special order finish, for more information please contact us on +44 (0) 845 605 4333.

Electropolishing

In various industries such as food, pharmaceutical and electronics, there is a requirement for easier cleaning and reduced bacterial growth on the surface of the stainless steel. This increased surface smoothness is achieved by a process called electropolishing.

Electropolishing is, in principle, a reversal of the electroplating process. The article is submerged in a special acid electrolyte and a DC current passed into the article and through the electrolyte. This process removes the high spots from the surface micro roughness leaving a surface which is bright and smooth.

6 Powder coated (E)

Powder coated finishes give excellent protection against scratches as they are normally between 50 - 100% harder than the equivalent wet paint finishes.

They are available in a wide range of colours and can have matt or various gloss finishes. In addition to the aesthetic qualities powder coating are available in various grades to cope with different site conditions. Grades are produced to cope with exterior applications where there can be high levels of ultra violet light or low smoke and fume applications for fire risk areas such as occur in tunnels. Because powder coated finishes are inherently resilient and resistant to chemical or corrosive attack, these finishes are frequently used for protection only where there is no aesthetic requirement.

Background

The process of powder coating is carried out by applying the electrostatically charged powder to the article, and then passing the article into an oven where the powder is baked onto the surface of the article.

The application of the powder, and the associated stoving, can vary with different types of finish so the careful control of the process is required.

Specification

With such a wide variety of types of powder available it is necessary to specify in addition to the colour what the finish is required to do.

The colour can be specified by BS or RAL number, or by exact colour match if a sample of the colour is provided. The required gloss level should also be given.

The usual finish is for aesthetic indoor use, but if other qualities are required they should be clearly indicated at the outset as the powder cost and application cost can vary considerably between different types of powder.

Epoxy coated

Epoxy coatings are based on thermo-setting epoxy resins and give a very hard, durable finish suitable for internal applications. Epoxy coatings are usually quite thin but they have good chemical resistance with excellent adhesion and coating flexibility.

Polyester epoxy mix

Some modern coating developments consist of both polyester and epoxy. These give properties which are very suitable for use with cable support systems. The finish is thick and fairly soft and gives good protection to the cables being installed. The coating has strong adhesive properties and in cases of fire is halogen free with low smoke and fume characteristics. There are many types and grades of these materials and when using them advice should be sought from our technical sales support team, please contact us on +44 (0) 845 605 4333.

Architectural powder coatings

These powder coatings are formulated to meet the particular requirements of exterior environments. They are inherently resilient and resistant to damage and chemical or corrosive attack, providing maximum protection to the substrate. When subjected to high levels of ultra violet light present within sunlight the coatings have excellent gloss retention and resistance to chalking. These coatings would normally be applied over a galvanised finish.